

# **CSK DEACTIVATOR**

## DESCRIPTION

CSK is a deactivating product that slow down the superficial setting of the concrete once placed on fresh concrete.

Is specific for CHROMOSTONE stone washed effect concrete floors .

# THECNICAL INFORMATION

- Quick dry
- Waterproof and anti-evaporating
- Reduced costs for smq
- 8 different colors to distinguish the depth of expsosition

| COLOUR   | AGGREGATES DIMENSION   | DEPTH OF EXPSOSITION   |
|--|--|--|
| BLU<br>BROWN<br>GREEN<br>YELLOW<br>PINK<br>GREY<br>WHITE | 0-4/8 mm<br>2-4/8 mm<br>4-8 mm<br>4-8 mm<br>6-8/12 mm<br>8-16 mm<br>8-16/22 mm | circa 0,5 mm<br>circa 1,0 mm<br>circa 1,5 mm<br>circa 2,0 mm<br>circa 2,5 mm<br>circa 3,0 mm<br>circa 4,0 mm |
| ORANGE   | 12-16/32 mm  | circa 5,0 mm   |

The wash depth may change according to the cement and water mix, the quantuty of cement used, the time elapsed befor the application of the deacivating product and the time elapsed bifore the wash.

#### INSTRUCTION

The product must be shaked well before the use, then sprayed on the concrete surface immidiately after the smoothening, paying attention to conver equally all the.

Whit a liter you can cover 6/7 mq.

The concrete surface must be smooth and without an excess of water .

We suggest the use of an airless gun with a diameter among 0,6 and 1,2 mm. The rain protection is assured after the CSK dry. The time needed to dry depends on the external temperature and the ammount of material used, it may take among 10 and 30 minutes. The choice if the right CSK deactivating must be



tested each time depending the mix, the concrete thickness and the size of the aggregates.

### WASHING

Wash the surface after 12-24 hours depending on the season and the weather conditions.

IMPORTANT:

What's in this data sheet is based on best knowledge derived from practical experience and laboratory. This document cancels and replaces the previous ones. The data can be modified at any time. The customer has the responsibility to verify that the product is suitable for the application they want to perform. The manufacturer assumes no responsibility for the results of incorrect applications. It is strongly recommended to test the product on a small area before application. The product is for professional use. The International Stone regularly organizes training courses for its customers who request it. Those who use these products without being entitled do so at their own risk.

Updated on: 12-6-09